

increasing height results from the fact that for tall dots the

hole states are of Γ_1 (S -like) symmetry. The Bloch part of the electron state is of Γ_1 symmetry in zinc-blende structure. The electron states in the following are therefore, including spin, twofold Kramer's degenerate. Furthermore, the contribution of the valence $|Z\rangle$ band in the hole states is neglected since it is pushed down in energy through the strong confinement in z direction (for flat dots). We will proceed in steps from the idealized cylindrical symmetry neglecting at first the spin-orbit interaction [Fig. 3 a)], to the full atomistic symmetry (C_{2v}) in the presence of the spin-orbit interaction [Fig. 3 d)]. We will show how the observed FS is the result of the atomistic symmetry in presence of the spin-orbit interaction.

Cylindrical symmetry, no spin-orbit interaction [Figs. 3 a) and 4 a)]. In this case, the hole states are eigenfunctions of the angular momentum $l=1$ as depicted in Fig. 4 a). The spin parts of the wave functions are written as $|\uparrow\rangle$ and $|\downarrow\rangle$. Due to the equivalence of the wave functions $|X\rangle$ and $|Y\rangle$ in cylindrical symmetry, the four hole states are degenerate. The resulting eight exciton states (two electrons, four holes) are split by the exchange interaction K (singlet-triplet splitting) into two $S=0$ and six $S=1$ states.

C_{2v} symmetry, no spin-orbit interaction [Figs. 3 b) and 4 b)]. The spin-independent C_{2v} potential does not have the ability to mix spins. However, it will mix the orbital parts of isospin hole states creating the eigenstates given in Fig. 4b, where the C_{2v} point-group notation¹⁷ has been used. We obtain two pairs of eigenfunctions whose orbital parts belong to the Γ_2 and Γ_4 representations and spin parts to the Γ_5 representation. The splitting of these two pairs is due to the nonequivalence of the $|\Gamma_{2v}\rangle$ and $|\Gamma_{4v}\rangle$ Bloch functions (atomistic asymmetry), reflected in the atomistic asymmetry parameter $\Delta = \langle \Gamma_{2v} | H_{C_{2v}} | \Gamma_{2v} \rangle - \langle \Gamma_{4v} | H_{C_{2v}} | \Gamma_{4v} \rangle$, which is characteristic of the C_{2v} potential. The previously fourfold degenerate hole states split into two by 2Δ . Consequently, the exciton states are split by the atomistic asymmetry 2Δ and further split into singlet and triplet by the exchange term K [Fig. 3 b)].

Cylindrical symmetry, with spin-orbit interaction [Figs. 3 c) and 4 c)]. The spin-orbit interaction splits the hole states with respect to their total angular momentum J . Thus, the $J_z=3/2$ hole states $a\uparrow$ and $b\downarrow$ will split by Δ_0 from the $J_z=1/2$ states $a\downarrow$ and $b\uparrow$ [see Fig. 4 c)]. Considering only the first two hole states ($a\uparrow$, $b\downarrow$) and the electron states ($e\downarrow$, $e\uparrow$), the exchange Hamiltonian in the basis of the four excitons ($a\uparrow e\uparrow$), ($a\uparrow e\downarrow$), ($b\downarrow$

